

PDC-12350

Deep Cycle AGM PDC Series - Deep Cycle AGM













Deep cycle AGM batteries engineered for long runtimes and repeated cycling. Rugged plate design and absorbent glass mat separators deliver dependable performance in applications such as mobility, marine, and renewables.

Configuration Options

PDC-12350 NB3

Performance Specs

Nominal Voltage 12.0 Volts, (6.0 cells)

Nominal Capacity

 20-hr. 31.2Ah (1.75A to 10.5 Volts)
 35.0Ah

 10-hr. 31.2Ah (3.12A to 10.5 Volts)
 31.2Ah

 5-hr. 28.85Ah (5.77A to 10.2 Volts)
 28.85Ah

 1-hr. 22.5Ah (22.5A to 9.6 Volts)
 22.5Ah

Approximate Weight25.68lbs, (11.65kg)VDS Weightlbs, (kg)

 Dimensions
 L: 7.68in, 195.0mm

 +/- 0.08 in. (+/- 2mm) for length, width, and height dimensions
 W: 5.12in, 130.0mm

 H: 6.46in, 164.0mm
 TH: 7.16in, 182.0mm

Internal Resistance (approx.) m Ω 10.0m Ω

Max Short Circuit Discharge Current 875.0A

Operating Temperature

Range

 $\begin{array}{ll} \text{Charge} & 32^{\circ}\text{F (0^{\circ}\text{C}) to } 104^{\circ}\text{F (}40^{\circ}\text{C}) \\ \text{Discharge} & -4^{\circ}\text{F (}-20^{\circ}\text{C) to } 131^{\circ}\text{F (}55^{\circ}\text{C)} \end{array}$


Case ABS

Recommended Power-Sonic Charger PSC-122000ACX

Available Terminals (mm)

TERMINAL POSTS

With nut & bolt connectors



Torque: 3.9~5.4 Nxm




Phone (US): (775) 825-6500

Phone (EMEA): +31 33 7410 700


Graphs

Capacity Retention SLA

CAPACITY RETENTION




PDC Cycle Life




SLA Charging

CHARGING CHARACTERISTICS @ C/5 AND 25°C



SLA Discharge Rates

Discharge Characteristics



Constant Current

VoltageOverTime	5min	10min	15min	20min	30min	45min	1h	1.5h	2h	3h	4h	5h	6h	8h	10 h	20h
1.60V/cell	141.3	91.4	67.8	53.4	38.5	27.8	22.5	16.2	12.6	8.91	6.98	5.92	5.05	3.96	3.22	1.79
1.65V/cell	134.5	88.4	66.0	52.1	37.7	27.3	22.1	16.0	12.4	8.8	6.68	5.85	4.99	3.93	3.19	1.78
1.67V/cell	133.2	87.7	65.5	51.8	37.5	27.1	22.0	15.9	12.3	8.75	6.85	5.82	4.98	3.91	3.18	1.78
1.70V/cell	128.7	85.3	64.0	50.8	36.9	26.7	21.7	15.7	12.2	8.66	6.79	5.77	4.94	3.88	3.15	1.76
1.75V/cell	122.9	82.0	61.9	49.4	36.0	26.1	21.3	15.4	12.0	8.54	6.7	5.7	4.88	3.84	3.12	1.75
1.80V/cell	116.7	78.8	59.9	48.0	35.1	25.5	20.8	15.1	11.8	8.4	6.61	5.62	4.82	3.79	3.09	1.73
1.85V/cell	108.5	74.4	57.1	46.2	34.0	24.9	20.4	14.8	11.6	8.27	6.51	5.54	4.75	3.74	3.05	1.71

Constant Power

VoltageOverTime	5min	10min	15min	20min	30min	45min	1h	1.5h	2h	3h	4h	5h	6h	8h	10 h	20h
1.60V/cell	252.2	167.3	126.2	100.5	73.0	52.8	43.0	31.2	24.3	17.3	13.6	11.6	9.92	7.82	6.37	3.6
1.65V/cell	244.7	164.0	124.0	98.8	72.1	52.1	42.4	30.8	24.0	17.2	13.4	11.4	9.83	7.74	6.31	3.56
1.67V/cell	242.4	162.5	122.9	98.0	71.4	51.8	42.3	30.7	23.9	17.1	13.4	11.4	9.81	7.72	6.29	3.55
1.70V/cell	236.2	158.9	120.3	96.3	70.3	51.1	41.7	30.4	23.7	16.9	13.3	11.4	9.72	7.66	6.25	3.53
1.75V/cell	227.8	153.9	117.1	94.1	68.9	50.2	41.1	29.9	23.4	16.7	13.2	11.2	9.62	7.59	6.19	3.5
1.80V/cell	218.6	149.0	114.0	92.0	67.5	49.3	40.4	29.5	23.1	16.5	13.0	11.1	9.53	7.52	6.14	3.46
1.85V/cell	205.2	141.6	109.3	89.0	65.7	48.2	39.6	29.0	22.7	16.3	12.8	10.9	9.39	7.42	6.06	3.43




Phone (US): (775) 825-6500

Phone (EMEA): +31 33 7410 700

Charging

Cycle Applications: Apply constant voltage charge at 2.35VPC – 2.45VPC (14.1 to 14.7 volts for 12V Monobloc) at 20°C. The initial charging current should be set at less than C/5 Amps. Switch to float charge when the current falls to a 3% capacity rate to avoid overcharging. Stand-By or "Float" Service: Apply constant voltage charge of 2.25VPC – 2.30VPC (13.5 to 13.8 volts for 12V Monobloc) at 20°C. When held at this voltage, the battery will seek its own current level and maintain itself in a fully charged condition. Temperature Compensation: Charging voltage for both cyclic and stand-by applications should be regulated in relation to ambient temperature. As temperature rises, charging voltage should be reduced to prevent overcharge and increased as the temperature falls to avoid undercharge. For further charging information, including temperature compensation factors, see the Power-Sonic Technical Manual.

Engineering Drawing



For Further Information

Please refer to our website, **www.power-sonic.com**, for a complete range of useful downloads, such as product catalogs, material safety data sheets (MSDS), ISO certification, etc.

Approvals



CE marking confirms a product meets EU safety, health, and environmental protection standards for battery and energy systems.



Conflict-free mineral certification ensuring ethical sourcing and transparent supply chain for responsible production.



Extended mineral reporting meets global supply chain transparency standards for responsible and ethical sourcing practices.



IEC 60896 standard ensures stationary lead-acid batteries meet safety, performance, and float charge application requirements.



ISO 9001:2015 certification ensures consistent quality management and manufacturing standards for energy storage products.



PFAS-free certification verifying environmentally responsible manufacturing of batteries and energy storage technologies.



California Proposition 65 compliant, providing consumer safety through reduced chemical exposure in battery manufacturing.



REACH compliant with EU chemical safety standards ensuring restricted substances are controlled in all battery components.



RoHS compliance ensures restriction of hazardous substances in electrical, electronic, and battery-powered products.



Sealed lead-acid batteries classified UN2800 nonspillable, certified safe for air, sea, and ground transport worldwide.



SVHC compliant with EU REACH regulations for Substances of Very High Concern used in electrical and energy storage products.



U.S. EPA TSCA compliance ensures toxic substances are regulated for safe manufacturing of batteries and electronic components.



UL 1989 certified for valve-regulated and vented lead-acid batteries used in UPS, emergency, and backup power applications.

